



CCW MiraDRAIN® 6000XL/6200XL DRAINAGE COMPOSITES

DESCRIPTION

CCW MiraDRAIN 6000XL/6200XL are high-performance, high-strength drainage composites consisting of a three-dimensional, high-impact polystyrene core, and a superior high-strength nonwoven filter fabric. CCW MiraDRAIN 6200XL has the added benefit of a polymeric sheet adhered to the back of the core, to prevent the drainage core from die cutting the waterproofing membrane. The filter fabric is bonded to the individual dimples of the molded polystyrene core to minimize fabric intrusion into the flow channels caused by backfill pressure. The fabric serves as a filter medium to prevent the passage of soil particles into the core while allowing subgrade moisture to pass freely.

TYPICAL USES

CCW MiraDRAIN 6000XL/6200XL are designed for use in high-flow, high-compressive strength, vertical drainage applications where single-sided subsurface drainage is needed.

CCW MiraDRAIN 6200XL is designed for use over CCW Waterproofing Membranes where extra protection is needed. The high-strength polymeric film adhered to the flat side of the drainage core provides additional factors of safety from potential die cutting into the waterproofing membrane.

The flat side of CCW MiraDRAIN 6000XL/6200XL fits directly against wall surfaces making them ideal for foundation walls, retaining walls, bridge abutments, and other similar structures. CCW MiraDRAIN 6000XL/6200XL also serves as a protection course over CCW Waterproofing Membranes.

FEATURES AND BENEFITS

- Relief of hydrostatic pressure buildup against subterranean surfaces.
- High-flow drainage capacity, with up to three times the flow capacity of aggregate or sand, assuring effective drainage for virtually any drainage need.
- No-clogging drainage performance.
- High compressive strength system that withstands installation and in-situ earth stresses.
- Enhancement of waterproofing system by channeling water away and providing a secondary water retention layer.
- Cost-saving, light weight, easy-to-install panels eliminate the need to bring aggregate to the construction site. CCW MiraDRAIN® also allows for backfilling with the same excavated soil.

INSTALLATION

GENERAL INFORMATION

CCW MiraDRAIN prefabricated drainage panels may be

installed in a variety of construction applications. They may be installed against retaining walls, foundation walls (both waterproofed and non-waterproofed), lagging systems and buttress/landfills. CCW MiraDRAIN can be cut with a utility knife or scissors. Slurries, shotcrete or concrete may be placed directly onto either side of the panels. The panels can terminate at the top of the footing and are flexible enough to form right angles to cover the top of the footing. CCW MiraDRAIN eliminates the need for a protection course over waterproofing systems. Native soils can be used over CCW MiraDRAIN. (Contact your local Carlisle Coatings & Waterproofing representative for specific guidelines).

FOUNDATION WALLS / VERTICAL APPLICATIONS

The CCW MiraDRAIN panel can be installed in rows or columns with the fabric side toward the soil. Each method has its advantages depending on the criteria of the project as to which method is best.

When installing the CCW MiraDRAIN in rows:

- Place the longitudinal edge of the core against the wall so that it is flush with the wall footing.
- Attach subsequent panels in shingle fashion, placing the longitudinal edge of the upper panel over the flanged longitudinal edge of the lower panel;

When installing the CCW MiraDRAIN in columns:

- Start at the low point of the wall and attach the panel to the wall.
- Adjacent panels should be joined together with the lateral edge of the connecting panel placed over the flanged edge of the previous panel;

The fabric from the adjacent panels should overlap the preceding panel. The fabric can be adhered with CCW DRAIN GRIP™ or duct tape. The top or terminal edge of the CCW MiraDRAIN should be sealed by wrapping the extra filter fabric around to the back side of the panel, to prevent soil or other foreign construction materials from intruding into or behind the panels. A “set back” or “ledge” condition may be encountered on some construction applications. Where this condition exists, CCW MiraDRAIN panels should be installed beginning at the bottom of the wall and ending at the ledge. Subsequent courses of CCW MiraDRAIN should be installed flat against the upper wall portion and placed so that 4-6” (10-15cm) extend down and over the lower edge. The overlapping CCW MiraDRAIN sections will be pushed flush against the wall during backfilling.

Attachment Method– No Waterproofing Membrane

The CCW MiraDRAIN should be attached to non-waterproofed walls with CCW DRAIN GRIP contact adhesive, CCW SecurTape tape or concrete nails. The CCW MiraDRAIN will be permanently secured upon comple-

tion of backfilling. Backfilling should be placed within two weeks. Backfill to at least 6" (15cm) above the top edge of the CCW MiraDRAIN.

Attachment Method– Using CCW MiraDRI 860/861, CCW 525, CCW Sure Seal, or CCW-500R Waterproofing Membranes

The CCW MiraDRAIN should be attached with CCW DRAIN GRIP contact adhesive or CCW SecurTape. Apply DRAIN GRIP around the panel edge and in 4" (10cm) ribbons on the back of the CCW MiraDRAIN and on the corresponding surface of the CCW Membrane. After the CCW DRAIN GRIP has been allowed to dry, mate the two surfaces together. The CCW MiraDRAIN will be permanently secured upon completion of backfilling. Backfilling should be placed as soon as possible. Backfill to at least 6" (15cm) above the top edge of the CCW MiraDRAIN.

Attachment Method– Using CCW MiraCLAY Waterproofing Membrane

The CCW MiraDRAIN should be attached over the CCW MiraCLAY membrane using concrete nails and washers.

Attachment Method– Soldier Pile Supported Excavations

The CCW MiraDRAIN should be secured with the appropriate fasteners for the substrate, i.e. concrete, masonry, wood or soil. Prevent concrete from flowing behind the CCW MiraDRAIN core by sealing the backside of the panel with duct tape or wood furring strip. Sealing the backside of the panel is not necessary if CCW MiraCLAY waterproofing membrane is applied over the CCW MiraDRAIN prior to pouring concrete or shotcreting. Voids in the soil or lagging that exceed 6" (150mm) across and 5" (12.5cm) deep must be filled to provide support for the CCW MiraDRAIN.

DRAINAGE COLLECTOR/DISCHARGE SYSTEM

Collector Pipe

Place CCW QuickDRAIN or collector pipe as required in design details. The CCW QuickDRAIN should be installed adjacent to the CCW MiraDRAIN. Care must

be taken to ensure a continuous drainage path between the CCW QuickDRAIN and the CCW MiraDRAIN panels. For installations where a collector pipe is specified, encapsulate the collector pipe in a gravel bed with a supplemental section of filter fabric as a separator/filter.

DETAIL REQUIREMENTS

For standard installation details, follow the CCW MiraDRAIN detail drawings. For non-standard installation instructions contact your local Carlisle Coatings & Waterproofing representative.

PACKAGING INFORMATION

Packaging: CCW MiraDRAIN 6000XL and 6200XL are available in rolls of 4' by 50' (1.22m by 15.24m).

CAUTIONS/LIMITATIONS

Limit ultra-violet exposure by backfilling within 7 days of installation. Any panels damaged during installation should be replaced by the installer.

Limitations: CCW MiraDRAIN is resistant to chemicals in normal soil environments. However, some reagents may affect its performance. Carlisle Coatings & Waterproofing representatives should be consulted concerning the suitability of CCW MiraDRAIN in unusual soil environments.

LIMITED WARRANTY

CARLISLE COATINGS & WATERPROOFING INCORPORATED (CARLISLE) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any CARLISLE materials prove to contain manufacturing defects that substantially effect their performance, CARLISLE will, at its option, replace the materials or refund its purchase price.

This limited warranty is the only warranty extended by CARLISLE with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. CARLISLE specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever.

The dollar value of CARLISLE'S liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the CARLISLE material in question.

TECHNICAL DATA

Property	Test Method	Unit	Typical Value
Core			
Thickness	ASTM D 1777	in (mm)	0.40 (10.16)
Compressive Strength	ASTM D 1621	psf (kPa)	16,500 (790)
Maximum Flow Rate ¹	ASTM D 4716	gpm/ft ² (l/min/m ²)	17 (211)
Installed Vertically ²	ASTM D 4716	gpm/ft ² (l/min/m ²)	14.5 (180)
Fabric (160N)			
Apparent Opening Size	ASTM D 4751	US Std Sieve (mm)	70 (0.21)
Water Flow Rate	ASTM D 4491	gpm/ft ² (l/min/m ²)	110 (4,477)
Grab Tensile Strength	ASTM D 4632	lbs (kN)	160 (0.71)
Grab Elongation	ASTM D 4632	%	50
Puncture Resistance	ASTM D 4833	lbs (kN)	95 (0.42)
System			
Performance Index	*		24,100

All flow rates were tested at 3600 psf.
¹In plane flow rate @ gradient of 1.0

* Drainage Performance Index is a function of ASTM D 4833, D 4632 and D 1621
²Installed flow rate with soil overburden at vertical gradient of 1.0

