



ATTACHMENT P-1

PAVER CRITERIA

Concrete Plaza pavers shall be a high density pressed concrete unit manufactured to +/-1/8" tolerance and produced by subjecting the concrete mix to a minimum pressure of 1,000 pounds per square inch over the entire surface area. Pedestals and shims used to elevate and adjust the pavers are recommended by Carlisle Coatings & Waterproofing. The paver should meet the following minimum physical properties:

Thickness	1 7/8" min.
Finish and Color	as specified by owner
Compressive Strength	7,500 psi min.
Water Absorption	< 5%
Density	155 lbs/cu ft
Flexural Strength	1,100 psi
Weight	23.5 lbs/sq. ft. min.