



# CCW-500 REINFORCING FABRIC

## DESCRIPTION

CCW-REINFORCING FABRIC is a 1.35 oz/square yard spunbonded polyester fabric used as the reinforcing layer in the CCW-500R Hot Applied Liquid Membrane System.

## APPLICATION

Apply the CCW-REINFORCING FABRIC while the first layer of CCW-500 is warm and tacky. The reinforcing fabric shall be applied without wrinkles and broomed to maximize adhesion to the first layer. Edges shall be overlapped a maximum of .5 inches. The reinforcing fabric shall be dry and free of dust prior to applying the second layer of CCW-500.

## PACKAGING

CCW-REINFORCING FABRIC is:  
59" X 610' (3,000 sf/roll ) 24 lb/roll; 15 rolls/pallet  
36" X 667' (2,000 sf/roll) 16 lb/roll; 15 rolls/pallet

## STORAGE

Store away from open flame, sparks, and welding. Protect from rain, dust, direct sunlight and harmful environmental conditions.

## LIMITED WARRANTY

CARLISLE COATINGS AND WATERPROOFING INCORPORATED (CARLISLE) warrants its materials to be free of manufacturing defects at the time of their delivery to the buyer. If any CARLISLE materials prove to contain manufacturing defects that substantially affect their performance, CARLISLE will, at its option, replace the material or refund the purchase price.

This limited warranty is the only warranty extended by CARLISLE with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. CARLISLE specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever.

The dollar value of CARLISLE's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the CARLISLE material in question.

### TECHNICAL DATA

PROPERTY	RESULTS
Weight	1.35 oz./yd <sup>2</sup>
Thickness	9 mils
Grab Tensile, MD	29 lbs.
Grab Tensile, XD	24 lbs.
Trapezoidal tear, MD	11 lbs.
Trapezoidal Tear, XD	12 lbs.
Mullen Burst	36 psi