



# CCW-5123-LO LOW ODOR INTERIOR VEHICULAR TRAFFIC DECK SYSTEM

## DESCRIPTION

The CCW-5123-LO Deck Coating System is a liquid-applied, abrasion resistant waterproofing system suitable for surfaces subject to interior vehicular and heavy pedestrian traffic. It consists of three polyurethane components, each designed to provide specific, long lasting properties, that together form a system with optimum performance. The Top Coat is available in two fade-resistant colors.

## TYPICAL USE

The CCW-5123-LO System is applied to interior concrete decks to prevent water from entering occupied space below, protect the surface to which it is applied from damage by water and salts and provide a slip-resistant, attractive wearing surface.

## LIMITATIONS

- Do not use on decks exposed ultra-violet rays.
- Do not apply primer or coatings to a frosty, damp or wet surface.
- Do not proceed with coating application if temperature is below 40°F or if rain is imminent within 8 hours after application. Cure time is slower in cool weather.
- Polyurethane coating cure times may be significantly faster than listed when temperature and/or humidity are high.
- If metal pan is used for concrete form, the pan must be vented. Not for use on grade.
- If deck has a between slab membrane, consult with Carlisle representative.
- Some high performance tires can stain a deck coating system. Carlisle cannot assume responsibility for stains from organic exposures, including staining deposits by high performance tires.
- Warn personnel against breathing of vapors and contact of material with skin or eyes. In confined areas, workmen shall wear approved respiratory protection gear and protective clothing. All gas flames and electrical apparatus shall be shut down prior to the start of and during coating applications. Provide adequate ventilation. Protect plants, vegetation, and animals which might be affected by the coating operation.

## PACKAGING

CCW-501-LO Base Coat, CCW-502-LO Intermediate Coat and CCW-503-AR-LO Top Coat: 5 gallon pails and 55 gallon drums.

CCW-501-T Detail Coat: 5 gallon pails

Shelf life: One year when stored at 85°F or below.

## APPLICABLE STANDARDS

ASTM C 957-93

## TOP COAT COLORS

Standard colors in stock include: Stone Gray and Colonial Gray. Additional standard and custom colors are available, minimum orders may apply.

## WARNINGS AND HAZARDS

*Before use refer to MSDS for important warnings and safety information. Use only in areas with adequate ventilation. Avoid breathing vapors. Keep away from heat and flame. Avoid contact with eyes and skin. In the event of skin contact, remove immediately and wash with warm, soapy water. Wear eye protection. Always wash hands before eating.*

## TYPICAL PROPERTIES\*

### CCW-501-LO BASE COAT

Solids Content	ASTM C 1250	85%
Hardness, Shore A	ASTM D 2240	63
Tensile Strength	ASTM D 412	850 psi
Ultimate Elongation	ASTM D 412	625%
Tear Resistance, Die C	ASTM D 624	140 lb/in
Adhesion to Concrete	ASTM D-903	23 PLI
Low Temp. Flexibility	ASTM D-522	-65°F

### CCW-502-LO INTERMEDIATE COAT

Solids Content	ASTM C 1250	80%
Hardness, Shore A	ASTM D 2240	82
Tensile Strength	ASTM D 412	2000 psi
Ultimate Elongation	ASTM D 412	425%
Tear, Die C	ASTM D 624	300 lb/in
Low Temp Flexibility	ASTM D-522	-65°F

### CCW-503-AR-LO TOP COAT

Solids Content	ASTM C 1250	72%
Hardness, Shore A	ASTM D 2240	91
Tensile Strength	ASTM D 412	3200 psi
Ultimate Elongation	ASTM D 412	190%
Tear, Die C	ASTM D 624	300 lb/in
Low Temp Flexibility and crack bridging**	ASTM C 957	Pass
Weather resistance	ASTM G 53	No chalking @ 2000 hrs
Abrasion resistance**	ASTM C 501	<50 mg.
Permeability**	ASTM E 96 (B)	<1.0 perms

\* Individual lots may vary +/- 10% from Typical value

\*\* System

## INSTALLATION

Surface should be properly sloped to drain freely and eliminate the ponding of water. The surface must be clean, dry and free of laitance, dirt, oil, grease or other contamination. Acceptable methods of cleaning are vacuum shotblasting, sandblasting, acid etching or mechanical

grinding followed by the complete and thorough removal of any residue.

If metal decking is used as a permanent form, the metal must be vented. If the deck is cast over precast tees or slabs, control joints should be placed directly over all joints per detail DC-1B. Surface shall have a steel trowel followed by a fine hair broom finish.

Saw-cut control joints and/or expansion joints shall have been properly installed at strategic points throughout the field of the deck to control cracking caused by deflection and shrinkage.

New concrete must be in place for 28 days minimum. Curing compounds must be of the self-dissipating type and be approved by the Carlisle representative. Old concrete must be structurally sound. Spalled areas shall be filled. Loose or deteriorated concrete shall be replaced. Abrade steel trowel finish by mechanical or chemical means. In the event of existing coatings, contact Carlisle.

Refer to Carlisle DC series details for proper detailing of cracks, drains, angle changes, parking bumpers, etc.

Saw cut cracks greater than 1/16" wide to 1/4" wide by 1/4" deep. Grind off high spots, ridges and fins. Fill all low spots, voids, rock pockets, excessively rough and spalled areas with approved non-shrink grout or epoxy patching compound.

Clean joints and saw cut cracks. All moving cracks over 1/16" wide and all expansion joints less than 1" wide shall be cleaned, primed, fitted with a backing rod and caulked with PT-304 or CCW-201 Sealant as recommended by the data sheet. For larger joints, contact Carlisle representative. Tool sealant flush in joints up to 1/2" wide, slightly concave on wider joints.

Any required metal or neoprene flashings should be installed at this time.

Apply a 1" face, 45 degree cant of sealant at all angle changes, including projections through the deck, walls, curbs, etc. Allow sealant to cure thoroughly.

Mix primer and apply per instructions below to all areas to receive a detail coat. Extend primer 2" past area to receive detail coat to allow primer tie-in during deck coating installation. Allow primer to dry 1 hour minimum, 8 hours maximum.

Apply a stripe coat of CCW-501-T Detail Coat, 30 mils thick, 6" wide, centered over all sealant cants, sealed cracks, hairline cracks around pipes and drains, control joints, expansion joints (less than 1/2" wide) and cold joints. Apply a stripe coat of CCW-501-T Detail Coat, 30 mils thick, 6" wide, centered over any transition between dissimilar materials, such as concrete to metal flashings, concrete to wood or wood to metal, and reinforce with CCW Reinforcing Fabric. Allow the stripe coat to cure over night (16 hours minimum). **Cauti-**  
**tion:** *Ensure that all sealant is thoroughly cured. Uncured sealant will affect the cure of the coating.*

**PRIMING:** Shall be CCW-557 (or CCW540 Water Based Epoxy) Primer. Stir each side separately to ensure that no separation has occurred then mix all of Part A with

all of Part B. Use a mixing paddle in a slow speed electric drill motor. Avoid air entrapment. Mix 2 to 3 minutes until a homogenous blend is achieved. Wait 15 minutes before applying.

Apply **CCW 557 (or CCW 540) Primer** at the approximate rate of 250-300 sq. ft. per gallon. Within 8 hours of application of the primer (16 hours for water-based primer), the base coat must be applied. If the base coat cannot be applied within this period, then reprime.

Primer is sufficiently dry when it is somewhat tacky but will not transfer when touched. In the event coating is not applied within the maximum time, reprime.

**BASE COAT APPLICATION:** Do not apply coating over joints greater than 1" wide. Wipe stripe coats to remove any dust or contamination. Apply CCW-501-LO in one uniform coat at the rate of one gallon minimum per 60 square feet or as needed in order to obtain a minimum thickness of 26 wet mils. Backroll for even coverage. Allow the base membrane to cure 16 hours minimum at 75°F.

**INTERMEDIATE COAT APPLICATION:** Apply CCW-502-LO in one uniform coat at the rate of one gallon minimum per 100 square feet or as needed in order to obtain a minimum thickness of 16 wet mils. Immediately broadcast 16 mesh silica sand into the wet CCW-502-LO at a rate of 10 to 12 lbs. per 100 sq. ft. Backroll to encapsulate the sand. Allow to cure 16 hours minimum at 75°F.

**EXTREMELY HIGH WEAR AREAS** such as ramps, tight turns and entrance/exit gates: After installation of CCW-502-LO as above, apply an additional coat of CCW-502-LO at the rate of one gallon minimum per 100 square feet. Uniformly broadcast 20 mesh sand over the surface at 15 to 25 lbs. per 100 sq. ft.

**TOP COAT APPLICATION:** Apply CCW-503-AR-LO in one uniform coat at the rate of one gallon minimum per 100 square feet or as needed in order to obtain a minimum thickness of 16 wet mils. Backroll for even coverage. Allow the CCW-503-AR-LO to cure at least 48 hours before opening the deck to vehicular traffic.

## LIMITED WARRANTY

CARLISLE COATINGS AND WATERPROOFING INCORPORATED (CARLISLE) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any CARLISLE materials prove to contain manufacturing defects that substantially affect their performance, CARLISLE will, at its option, replace the material or refund the purchase price.

This limited warranty is the only warranty extended by CARLISLE with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. CARLISLE specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever.

The dollar value of CARLISLE's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the CARLISLE material in question.

Carlisle Coatings & Waterproofing Incorporated  
900 Hensley Lane  
Wylie, Texas 75098  
Toll Free: (800) 527-7092  
Website: [www.carlisle-ccw.com](http://www.carlisle-ccw.com)

